
Contingency Evaluation



"Supporting DOD Operations Worldwide"

Don R. Alexander
Chief, Airfields and Pavements Branch
US Army Engineer Research and Development Center
Vicksburg, MS

Tel: 601-634-2731 Email: don.r.alexander@erdc.usace.army.mil





Structural Suitability in a Contingency Environment

 Units Tasked to Conduct Contingency Evaluations and Lessons Learned

Mr. Richard Smith
Air Force Civil Engineering Support Agency (AFCESA)

 Procedures for Structural Assessment of Contingency Airfields

Mr. Richard Smith
Air Force Civil Engineering Support Agency (AFCESA)

Equipment Technology for Pavement Assessment

Mr. Don R. Alexander
US Army Engineer Research and Development Center (ERDC



Dynamic Cone Penetrometer (DCP)


- Simple Device, Easy to Use
- No Electronics/Batteries Required
- Capable of Penetrating Stiff Layers
- Correlations Established For Estimating CBR






Standard Test Method for Use of the Dynamic Cone Penetrometer in Shallow Pavement Applications¹






DCP VS CBR CORRELATIONS



Dynamic Cone Penetrometer (DCP)





Blows	<u>Penetration</u>
0	0
3	1.6
3 3 3	3.9
3	5.8
3	8.2

APE Evaluation

DCP - UFC Manual 3-260-3 Page 3-6

DCP DATA SHEET

Project: MAY FORT Site: STATION R-550 L Test Location: RIA

Date: 12/5/01

Project: MAY PORT
Site: 5TA - 550 R
Test Location: 足いぬ
Date: 12 5 (0)

Project: may poet Site: 5TA - 550 C Test Location: R1A Date: \2\5/01

Number	Accumulative	
of	Penetration	
Blows	(mm)	
G	23	
10	55	
10	86	
lo	115	
10	147	
10	180	
10	212	
10	245	
10	<u> </u>	
10	306	
5	326	
5	350	
_ 5	377	
_ <u>5</u>	414	
3	455	
5	490	
5	529	
5	567	
5	602	
5	641	
3	678	
3	217	
3	757	
3	808	
3	858	
3	904	
3	959	
3	1010	
3	1063	
3	1109	
3	1159	
3	1208	

Number	Accumulative
of	Penetration
Blows 0	(mm)
0	25
10	54
10	85
10	115
10	144
ιο	183
10	210
10	243
10	278
10	307
5	325
	347
5	378
5	411
5	451
5	491
5	531
5	565
5	608
5 7	645
3	678
3	720
3	750
3	800
3	953
3	900
3	950
3	1008
3	1060
3	1111
3	1161
3	1211

Number	Accumulative
of	Penetration
Blows	(mm)
0	26 58
ſο	58
10	91
10	123
10	152
10	185
10	220
10	252
0	264
<u>lg</u>	280
5	330
5	360
5	385
5	420
5	461
5	4 <i>85</i> 535
5	535
	572
5	610
5	651 685
- 7	685
2	725
	763 818
3	818
_3	865
_3	911
3	963
3	1017
3	1070
3	1115
3	1165
3	1212



Perform Field Tests Automated DCP




Manual operation


Latest version of DCP, developed to facilitate evaluation of semi-prepared airfields for C-17 operations, reduces manpower required to perform to one person.



Automated data collection








DCP - UFC Manual 3-260-3 Page 3-6 & 3-7


CBR VS BEARING VALUE



Larger Devices (Poor Logistics)

- Automated DCP
 - Layer thickness
 - Layer Strength
- Electronic Cone Penetrometer
 - Layer thickness
 - Layer Strength
- Falling Weight Deflectometer
 - Pavement stiffness
 - Material properties (moduli)
- Ground Penetrating Radar
 - Layer Thickness
 - Underground utilities
- Ladar
 - Rut Depth
 - Roughness





Perform Field Tests Automated DCP Truck

Automatically operated hammer drives tip into soil

Correlates to CBR









Perform Field Tests Electronic Cone Penetrometer



- ECP correlation classifies soil type and layer thickness & strength
- Typically penetrate 5 10 feet












NDT




- Analyzing test data using various plots
- Assigning Test Data to Feature
- Statistics
- Multiple Drop/Lane filtering

Ground Penetrating Radar

Developed by
Pulse Radar, Houston, TX
under SBIR Contract
(Two Systems Delivered to WES)









Color Coded GPR Signal

CROUND PENETRATING RADAR SURVEY




GPR Survey of Road at WES






Depth (Thickness)

Forest Service Road - Items 12-7



Depth, in


Ground Penetrating Radar




Phase-Measurement Laser Radar (Ladar)



The Airfields and Pavements Branch of the Engineer Research and Development Center is developing applications for a new measurement sensor developed under an Army SBIR by Phoenix Scientific, Inc. (PSI)










Road Survey – GPR, Ladar, ARRK






Phase-Measurement Laser Radar (Ladar)







Smaller Devices Under Development/Testing

- Geogauge
 - Pavement stiffness
- Portable Falling Weight Deflectometer
 - Pavement stiffness
- Portable Seismic Test Equipment
 - Layer thickness (top layer)
 - Modulus (top layer)
- Extended PSPA
 - Layer thickness (top meter)
 - Modulus (top meter)
- Free-Free Resonance Testing
 - Modulus (core)



GeoGauge – Stiffness & Modulus





GeoGauge

<u>Humboldt GeoGauge</u>:

Physical Attributes

Size: 11" OD x 10" tall

> 4.5" OD x 3.5" ID Foot

➤ Weight: 22 lb

Powered by 6 D-Cell Batteries

Keypad User InterfaceSpecification

Stiffness: 3 (17) to >70 (399) MN/m (klb/in)

Young's Modulus: 26.2 (3.8) to > 607 (88) MPa (kpsi)

> Poisson's Ratio: Variable in 0.05 Increments

Precision: Typically 3.9% Coefficient of Variation

➤ Bias: < 1: Coefficient of Variation

Depth of Measurement: 22.9 cm (9 in)

Battery Life: >1500 measurements

Operating Temperature: 0 C to 38 C (32 F to 100 F)






GeoGauge

Operating Principle

- Stiffness to Modulus (Young's, E)
 - Measures Stiffness
 - > Through Foot Radius and Poisson's Ratio Obtain Modulus



- Rigid foot with annular ring
- 2 Rigid cylindrical sleeve
- 3 Clamped flexible plate
- 4 Electro-mechanical shaker
- 5 Upper velocity sensor
- 6 Lower velocity sensor
- 7 External case
- 8 Vibration isolation mounts
- 9 Electronics
- 10 Control & display
- 11 Power supply

 $E(MPa) = P*(1-v^2)*b/r/d$

where

P/d = the SSG stiffness reading (MN/m)

= Poisson's ratio (assumed to be 0.35 for all materials tested)

r = radius

b = $2*a/\Pi$ (a = 0.89 for a rigid ring with radius ratio = 1.3)

Portable Falling Weight Deflectometer





Devices Evaluated - PFWD

Keros Prima 100 Portable Falling Weight Deflectometer:

Physical Attributes

- Weight: 26 kg
- ➤ 10-20 kg Falling Mass
- Adjustable Falling Height of 0-850 mm
- Adjustable Falling Mass of 10, 15, or 20 kg

Specification

- Selection of Loading Plate
 - 300 mm: Subgrade, earth filling, subbase, gravel base layer
 - > 200 mm: gravel base layer, weak road structures
 - > 100 mm: Strong road structures
- Operating Temperature: 5 C to 50 C (41 F to 122 F)
- Expected Measuring Range Modulus (Young's, E)

> Subgrade: 5-60 MPa

Subbase: 25-75 MPa


Gravel Base Layer: 40 - 125 MPa


Asphalt: 100-300 MPa







Preliminary Results











Preliminary Results





Preliminary Results






Portable Seismic Pavement Analyzer








PSPA Vs. Flexural Strength




Extended PSPA Under Development



- Partnering With Geomedia (El Paso)
- Folds to Fit into rucksack
- Less than 35 lbs
- Samples to 1-Meter Depth
- Faster and Quieter Than DCP








Free-Free Resonant Column



FF Vs. Flexural Strength (Sawn Beams)





Future

- Army Small Business Innovative Research (SBIR)
 - Stiffness measurement from a moving platform
 - Autonomous data collection systems



Contingency Evaluation Workshop

Questions??

